


2 ENTRIES
3 ENTRIES
4 ENTRIES
5 ENTRIES
MULTI-ENTRY SEALS

Ref.	Suitable for		n° entries	Ø Dia entry (mm)	Quantity Box/Bag
	MAXIblock®	MAXIbrass® MAXIinox			
36A3M1623	M16 + Pg11	M16 + Pg11	2	3	1.500/100
36A3M1624	M16 + Pg11	M16 + Pg11	2	4	1.000/100
36A3M16322	M16 + Pg11	M16 + Pg11	3	2,2	1.500/100
36A3M2025	M20 + Pg13,5	M20 + Pg13,5 + Pg16	2	5	500/100
36A3M2034	M20 + Pg13,5	M20 + Pg13,5 + Pg16	3	4	500/100
36A3M20356	M20 + Pg13,5	M20 + Pg13,5 + Pg16	3	5,6	500/100
36A3M2526	M25	M25 + Pg21	2	6	300/50
36A3M2536	M25	M25 + Pg21	3	6	300/50
36A3M2537	M25	M25 + Pg21	3	7	300/50
36A3M2545	M25	M25 + Pg21	4	5	300/50
36A3M2546	M25	M25 + Pg21	4	6	300/50
36A3M2554	M25	M25 + Pg21	5	4	300/50
36A3M3228	M32	M32	2	8	150/50
36A3M32465	M32	M32	4	6,5	150/50
36A3M3248	M32	M32	4	8	150/50
36A3M4078	M40	M40	7	8	100/100
36A3M40106	M40	M40	10	6	100/100
36A3M5088	M50	M50	8	8	50/50
36C201629	Pg16	-	2	3+9	400/50

Technical features:

MATERIAL
HARDNESS
DENSITY
BREAKING RESISTANCE
BREAKING ELONGATION
TEARING
OPERATING TEMPERATURE

COMPRESSION SET (24 hours at 100°C sch.25%) ASTM D 395 B

Reference Norm:

ASTM D 2240
ASTM D 1817
ASTM D 412
ASTM D 412
ASTM D 624

NEOPRENE® (CR) rubber
70 SHORE A
1,358 gr/cm³
15 N/mm² (Mpa)
300%
25 N/mm
-40°C ÷ +120°C (continuous)
+130°C (short periods)
19%

Chemical and physical resistance of the material:

FUEL and PETROL - critical
GREASES and VEGETABLE OILS - sufficient
LIQUID PARAFFIN - sufficient
TURPENTINE - critical
DILUTED ACIDS - not critical
CHLORINE - not critical
NORMALLY CHLORINATED WATER - not critical
SEA WATER - not critical
DILUTED ALKALI - not critical
AGING - not critical
OZONE 70 hours with elongation of 10% at 38°C ozone 50 pphm

Cembre SpA

Via Serenissima, 9 - 25135 Brescia (Italy)
Tel.: +39 030 36921 - Fax: +39 030 3365766
Web: www.cembre.com - Email: info@cembre.com